

# Applying Scuffmaster ScrubTough™ Finish

---

## Products

Scuffmaster ScrubTough is a waterbased polyurethane-fortified eggshell coating. It is a two-component system that must be crosslinked with Masterlink™ crosslinker immediately prior to application.

---

## Product Preparation

Prior to application, box all cans/pails of the same color. If thinning is required, follow directions on product labels. All Scuffmaster products must be crosslinked with Masterlink according to instructions on product labels.

---

## Preparing to Application

Ensure good lighting conditions and ventilation of spray mist (if spraying). **Thoroughly protect finished spaces and surfaces from spray mist!** Apply products only when temperature is between 50° F - 80° F and drying conditions are good.

---

## Coverage Rates

The approximate coverage rate for Scuffmaster ScrubTough is 350 square feet per gallon on a smooth, sealed surface. Bright, deep or dark colors will require at least two coats.

---

## Safety First!

Some persons may experience an allergic reaction to paint products if exposed to spray mist. Because spray application of this Scuffmaster finish will create a fine mist of product and crosslinker in the immediate application area, a high-efficiency particulate respirator and protective goggles should be worn by the applicator. The immediate application area should be “cautioned off” to prevent persons without safety equipment from coming into contact with spray mist. Ensure good ventilation. Product MSDS sheets are shipped with every order and are also available from MCT by calling (800) 898-0219.

---

## Application Technique

**Brushing:** No thinning necessary. Use a nylon/polyester brush.

**Rolling:** No thinning necessary. Use a 3/8” nap synthetic roller cover.

**Airless Sprayer:** Up to four ounces of water/gallon. Pressure – 2000 psi. Tip - .015”-.021”.

**Conventional Sprayer:** Not recommended.

**CAUTION!** When spraying, wear goggles and a high-efficiency particulate respirator. Caution-off the immediate application area to prevent others from coming into contact with spray mist.

If you have additional application questions, please call MCT Technical Support weekdays between 8 a.m. and 5 p.m. CST at (800) 898-0219.